

HEAT SHRINK WRAP

9 MIL FLAME RETARDANT WHITE POLY SHEETING



PRODUCT DESCRIPTION

Americover's Shrink Wrap is suited for heavy-duty applications where excellent two directional shrink properties and toughness is required. Our Shrink Wrap is formulated from premium grade polyethylene, UV inhibitors, and other additives, which are designed to resist degradation due to sunlight, rain, chemicals, and heat. Americover's Shrink Wrap is manufactured to the highest QC standards and is backed by a proven track record of success.

-Meets the requirements of NFPA 701 (2004) Test 2 Flammability

APPLICATIONS

- ▶ Scaffolding Wrap for buildings
- ▶ Temporary Roof Cover after natural disasters
- ▶ Modular Home wraps and cover
- ▶ Large Building Frame wrap
- ▶ Storage Cover for Large Machinery with sharp protrusions
- ▶ Transportation cover of large or medium sized machinery.
- ▶ Industrial containment of plant equipment/components
- ▶ Other applications that require a fire retardant film

PRODUCT USE

You will need a hand held heat tool to start the biaxial shrinking process. Once the film has been heated it turns into in a "drum-tight" protective covering. We recommend padding sharp, protruding edges to prevent damage during installation. **PLEASE NOTE: FLAME RETARDANT SHRINK WRAP CAN STILL IGNITE. THEWRAP CONTAINS SPECIAL ADDITIVES THAT WILL SELF-EXTINGUISH.**

SIZE AND PACKAGING

Please call for roll sizes.

PROPERTIES	TEST METHOD	Nominal Values
Thickness	ASTM D374	9 Mil
Tensile Properties	ASTM D882	-
Yield (md/cd)	-	1400/1200 psi
Break (md/cd)	-	2500/2400 psi
Elongation (md/cd)	-	600/700 %
Dart Impact	ASTM D1709	750 grams
Elmendorf Tear (md/cd)	ASTM D1922	1200/1500 grams
Shrink Temperature	ASTM D2732	275° F

NOTE: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. AMERICOVER, INC. MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.Americover.com

DS.042417.061917