



DURA-SKRIM® 8BB & 8WB

FOUR-LAYER REINFORCED EXTRUSION LAMINATE



PRODUCT DESCRIPTION

DURA-SKRIM® 8BB and 8WB consist of two sheets of high-strength polyethylene film laminated together with a third layer of molten polyethylene. The white outer layer (DURA-SKRIM® 8WB) contains UV inhibitors and thermal stabilizers and the black outer layer(s) contains carbon black to enhance outdoor life. The white outer surface is also designed to reduce heat build up and condensation. DURA-SKRIM® is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions.

APPLICATIONS

- ▶ Cargo Coverings
- ▶ Interim Landfill Covers
- ▶ Daily Landfill Covers
- ▶ Temporary Erosion Control
- ▶ Divider Curtains
- ▶ Crawlspace Encapsulation
- ▶ Remediation Covers or Liners
- ▶ Pit/Pond Liners
- ▶ Underslab Vapor Retarders
- ▶ Temporary Earthen Liners
- ▶ Temporary Rainshed Covers

PRODUCT USE

DURA-SKRIM® 8BB and 8WB are used in more demanding applications requiring high tear resistance. Please inquire about DURA-SKRIM® 8BV and 12BV for longer-term applications up to 5 years, meeting GRI-GM22 Standard Specifications for Scrim Reinforced Geomembranes Used in Exposed Temporary Applications.

SIZE AND PACKAGING

DURA-SKRIM® R8BB and R8WB, are available in a variety of widths up to 180,000 square feet. All panels are manufactured in a quality controlled environment and are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time-saving installation.



800.747.6095
760.747.6095



Inquiries@americover.com
www.americover.com



2067 Wineridge Place, Suite F • Escondido, CA 92029



DURA-SKRIM®

SPECIFICATIONS



		DURA-SKRIM® 8BBR / 8WBK	
PROPERTIES	TEST METHOD	IMPERIAL	METRIC
Appearance		Black/Black or White/Black	
Thickness/Nominal	ASTM D5199	8 mil	0.20 mm
Weight	ASTM D751	37 lbs/MSF	181 g/m ²
Construction		Extrusion laminated with scrim reinforcement	
² Grab Tensile Strength	ASTM D7004	80 lbs	356 N
² Grab Tensile Elongation	ASTM D7004	17 %	17 %
³ Tongue Tear	ASTM D5884	30 lbs	133 N
CBR Puncture Resistance	ASTM D6241	200 lbs	890 N
Mullen Burst	ASTM D751	78 psi	538 kPa
WVTR	ASTM E96	0.016 grains/ft ² •hr	0.268 g/m ² •day
Perm Rating	ASTM E96	0.039 Perms	0.026 g/m ² •day•mm Hg
Hydraulic Conductivity	ASTM E96	3.14x10 ⁻¹⁰ cm/sec	
Maximum Static Use Temperature		180° F	82° C
Minimum Static Use Temperature		-70° F	-57° C

² Tests are an average of primary reinforcement directions.

³ Tests are an average of machine and transverse directions.

DURA-SKRIM® R8BB and R8WB consist of two sheets of high-strength polyethylene film laminated together with a third layer of molten polyethylene. The white outer layer (DURA-SKRIM® R8WB) contains UV inhibitors and thermal stabilizers and the black outer layer(s) contains carbon black to enhance outdoor life. The white outer surface is also designed to reduce heat build up and condensation. DURA-SKRIM® is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions.

NOTE: The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, express or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.

RI.062817.020518